



P-17
HIGH HEAT
RESISTANT
RIGID FILLER
GREY, BLACK, WHITE

PRODUCT BULLETIN



www.CASSpolymers.com
31200 Stephenson Hwy

800.344.7776
Madison Heights MI 48071

ADTECH@CASSpolymers.com
Ph 248.588.2270 Fax 248.588.5909

DESCRIPTION

P-17 high heat resistant filler set-fast system has uses in aerospace, aircraft, automotive, tooling, manufacturing and final fabrication where potential exposure to elevated temperatures up to 230°C/446°F have to be tolerated either for short term or continuous periods. P-17 offers the user a smooth workable paste with set-fast cure to expedite those applications for repair or finish. P-17 can be applied with a squeegee, spatula or flat tool. The cured material can be finished by mechanical sanding, grinding, scraping, etc., to a feather edge. This filler has excellent adhesive and bond strength to fiberglass, SMC, BMC, RIM, FRP, epoxy, graphite and Kevlar® composites as well as aluminum, plaster and other substrates. P-17 high heat resistant filler when cured and finished accepts virtually all types of coatings and decorative film without any blush or discoloration. **Typical applications include: Aircraft interior panels, FRP panels-filling cloth imprint, nose cone porosity, edge filling on honeycomb, changes & repairs to vacuum form molds, drill fixtures, potting bushings, gel-coat repairs on production molds, SMC mold porosity in molded parts, and many other applications.**

HANDLING CHARACTERISTICS @ 25°C/77°F

Mix Ratio (parts by weight or volume).....	100R/2H
Mixed Consistency	Creamy Paste
Density	12.75 lbs/gal
.....	0.055 lbs/cu in
Work Life (100 gram mass)	5-7 minutes
Finish Schedule (100 gram mass)	15 minutes
Hardness.....	80 Shore D
Shelf Life (in original unopened containers).....	1 Year
Storage Requirement.....	40°F - 80°F

PHYSICAL PROPERTIES

Tensile Strength (ASTM D-638.91).....	4074 psi
Tensile Elongation (ASTM D-638.91).....	1.163%
Flexural Strength (ASTM D-790.92).....	7080 psi
Compressive Strength (ASTM D-695.91)	8992 psi
Shrinkage (Cast Bar)(ASTM D-2566.86)	0.00982 in/in
Coefficient of Linear Thermal Expansion (ASTM D-696.91)	25.4 x 10 ⁻⁶ in/in°F
Water Absorption after 24 hours immersion in distilled water (ASTM D-570)	0.149%

NOTE: All high heat resistant systems typically exhibit a slight color change at the extreme end of the elevated temperature range when used in tooling repairs.

MIXING INSTRUCTIONS

Stir contents of can thoroughly using a spatula or putty knife. Place the required amount of filler and cream hardener on a disposable clean surface. Mix 100 parts paste to 2 parts BPO cream hardener by weight; i.e. size of golf ball (paste) to a two inch strip of BPO catalyst. Set up time of mix at room temperature will be 5-10 minutes and may be adjusted faster or slower by increasing or decreasing the amount of hardener, the use of too much hardener can cause gumminess in the filler. After 15-20 minutes the filler may be filed or sanded to final finish.

® Registered trademark of E.I. DuPont deNemours

P-17 Tech/Revised 4/12/11
Supersedes 9/1/09

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the products failure to conform to any particular specifications.