

	Density	Core Shear		Core Compressive		Flatwise Tensile	Flexural Properties		Water Absorption
	ASTM C271	ASTM C273		ASTM C365		ASTM C297	ASTM D790		ASTM C272
	(lb/Ft <sup>3</sup> ) / (kg/m <sup>3</sup> )	Strength	Modulus	Strength	Modulus	Strength	Strength	Modulus	%by Weight
		(psi) / (MPa)	(psi) / (MPa)	(psi) / (MPa)	(psi) / (MPa)	(psi) / (MPa)	(psi) / (MPa)	(psi) / (MPa)	
<b>Bluewater 26</b>									
0.50" / 12 mm	26 / 416	550 / 3.8	2,050 / 14.1	800 / 5.5	13,980 / 96.4	690 / 4.8	5,260 / 36.3	265,300 / 1,829	1.1
0.75" / 20 mm	26 / 416	530 / 3.7	4,220 / 29.1	820 / 5.7	11,810 / 81.4	480 / 3.3	4,960 / 34.2	242,900 / 1,675	
1.50" / 38 mm	26 / 416	520 / 3.6	6,300 / 43.4	1,060 / 7.3	31,050 / 214.1	510 / 3.5	4,010 / 27.6	215,100 / 1,483	
<b>Bluewater 20</b>									
0.50" / 12 mm	20 / 320	410 / 2.8	3,640 / 25.1	510 / 3.5	9,150 / 63.1	380 / 2.6	3,860 / 26.6	188,700 / 1,301	
0.75" / 20 mm	20 / 320	420 / 2.9	4,660 / 32.1	410 / 2.8	7,270 / 50.1	440 / 3.0	2,830 / 19.5	166,000 / 1,145	
1.50" / 38 mm	20 / 320	500 / 3.5	6,360 / 43.8	660 / 4.6	19,460 / 134.2	570 / 3.9	2,750 / 19.0	135,000 / 931	
<b>Nautical 24</b>									
0.50" / 12 mm	24 / 384	650 / 4.5	3,990 / 27.5	980 / 6.8	16,830 / 116.0	550 / 3.8	3,430 / 23.6	114,700 / 791	0.75
0.75" / 20 mm	24 / 384	630 / 4.3	5,630 / 38.8	630 / 4.3	9,330 / 64.3	660 / 4.6	2,910 / 20.1	99,100 / 683	
<b>Nautical 20</b>									
0.50" / 12 mm	20 / 320	450 / 3.1	2,970 / 20.5	600 / 4.1	13,340 / 92.0	600 / 4.1	2,700 / 18.6	91,700 / 632	
0.75" / 20 mm	20 / 320	510 / 3.5	3,740 / 25.8	740 / 5.1	15,710 / 108.3	630 / 4.3	2,430 / 16.8	71,800 / 495	
1.50" / 38 mm	20 / 320	420 / 2.9	5,220 / 36.0	530 / 3.7	19,390 / 133.7	520 / 3.6	2,310 / 15.9	75,200 / 519	
<b>Nautical 15</b>									
0.50" / 12 mm	15 / 240	410 / 2.8	2,680 / 18.5	400 / 2.8	7,130 / 49.2	340 / 2.3	2,220 / 15.3	83,900 / 578	

\*ASTM D790 - 3 point Bending, L/D-16/1

Important! The information and data presented herein are based upon information reasonably available to Coosa Composites, LLC from independent testing labs at the time of publication and are presented in good faith, but are not to be construed as guarantees or warranties, express or implied, regarding performance, results are to be obtained from use, comprehensiveness, and merchantability. You should thoroughly test any application, and independently determine satisfactory performance before commercialization or use.