

Trilux 33 Aerosol

Antifouling

Antifouling Paint for Outdrives and Outboards



PRODUCT DESCRIPTION

Trilux 33 Aerosol antifouling paint is formulated specifically for aluminum outboards, outdrives and aluminum hulls in underwater areas. Trilux 33 Aerosol uses two biocides and Biolux technology for protection from all types of fouling. Biolux technology is used to control slime growth. Trilux 33 Aerosol is for use in fresh, salt and brackish water.

PRODUCT INFORMATION

Color	YBA063A-White, YBA064A-Gray, YBA068A-Black
Finish	Matte
Volume Solids	14%
Typical Shelf Life	2 yrs
VOC (As Supplied)	470 g/lit
Unit Size	16 fl.oz

DRYING/OVERCOATING INFORMATION

Drying									
		41°F (5°C)		50°F (10°C)		73°F (23°C)		95°F (35°C)	
Touch Dry [ISO]		45 mins		30 mins		30 mins		30 mins	
Immersion		24 hrs		16 hrs		12 hrs		8 hrs	
Overcoating									
Substrate Temperature									
		41°F (5°C)		50°F (10°C)		73°F (23°C)		95°F (35°C)	
Overcoated By		Min	Max	Min	Max	Min	Max	Min	Max
Trilux 33 Aerosol		18 hrs	-	12 hrs	-	6 hrs	-	4 hrs	-

APPLICATION AND USE

Preparation	<p>BARE ALUMINUM Grind or blast the bare aluminium to a bright metal finish. For best results pre-prime using an etch primer. Remove sanding residue or any dust. Immediately apply at least 3 coats of Interprotect 2000E (first coat thinned 10 - 15%) or one full can of Primocon Aerosol Primer YPA985 in a multi-layer procedure.</p> <p>PREVIOUSLY PAINTED SURFACES</p> <p>with Trilux 33 Aerosol or Trilux Prop & Drive Sand with 80 grade (grit) paper.</p> <p>with Factory Finish or Antifouling Paint Sand with 80 grade (grit) paper. Clean with Special Thinner 216. Resand any areas where bare aluminium is exposed with medium grade (grit) emery cloth and wipe clean. Follow procedure for bare aluminium above.</p> <p>EPOXY Remove all surface contamination using Fiberglass Surface Prep YMA601, flush with fresh water and allow to dry. Sand with 80 grade (grit) paper. Remove sanding residue. Wipe with Fiberglass Solvent Wash 202. Apply Interprotect 2000E as primer.</p>
Method	At least 2 coats should be applied. Hold can 12-16 inches from the unit when applying the paint. Wait for minimum overcoating time between coats. Continue until the entire can has been used per outdrive. Be sure the paint is completely dry before immersion and allow minimum immersion time.
Hints	<p>Mixing Shake can well, listen for mixing ball & continue shaking vigorously for at least 2 minutes. It is best to shake in an up and down motion. IF CAN IS NOT SHAKEN PROPERLY CLOGGING OF THE TIP MAY RESULT.</p> <p>Other Put extra coats of Trilux 33 Aerosol on the props and other running gear. For best antifouling protection use entire can of Trilux 33 Aerosol for each lower unit. Further material may be required for larger units.</p>
Some Important Points	Product temperature should be minimum 10°C/50°F and maximum 29°C/85°F. Ambient temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Substrate temperature should be minimum 10°C/50°F and maximum 29°C/85°F.
Compatibility/Substrates	Apply to clean, dry, properly prepared surfaces only.
Number of Coats	2
Coverage	(Theoretical) - 21.2 ft²/gal
Recommended DFT per coat	2 mils dry
Application Methods	Aerosol can

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

Trilux 33 Aerosol

Antifouling

Antifouling Paint for Outdrives and Outboards



Storage

TRANSPORTATION:

Trilux 33 Aerosol should be kept in securely closed containers during transport and storage.

STORAGE:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Trilux 33 Aerosol to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

Safety

DISPOSAL:

Container Disposal: Triple Rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill or by other procedures approved by state or local authorities. Pesticide Disposal: Open dumping is prohibited. Pesticide, spray mixture or rinsate that cannot be used or chemically reprocessed should be disposed of according to procedures approved by Federal, state, or local disposal authorities.

GENERAL:

Read the label safety section for Health and Safety Information, also available from our Technical Help Line. Contains biocides. Antifoulings should only be wet sanded. Never dry sand or burn-off old antifoulings.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.